

The application was originally made under the Patent Cooperation Treaty with the Soviet Union Patent Office acting as the receiving office on (86) 19 Jun 1980, being given an application number PCT/SU80/00104. The application was searched by the Soviet Union Patent Office acting as the International Search Authority (ISA), and published by the International Bureau on (87) 14 May 1981 under serial number WO81/01290 in the Russian language. The text of the application is contained in the publication made by the International Bureau as above identified. The accompanying text being an English translation thereof.

(12) UK Patent Application (19) GB (11) 2 114 578 A

- (21) Application No 8120002
 (22) Date of filing
 19 Jun 1980
 (30) Priority data
 (31) 2831351
 2912552
 2912551
 (32) 6 Nov 1979
 28 Feb 1980
 28 Feb 1980
 (33) Soviet Union (SU)
 (43) Date of issue
 24 Aug 1983
 (51) INT CL³ (AS GIVEN BY
 ISA) C08F 220/56 C08L
 33/26
 (52) Domestic classification
 C3L DF
 C3P JG
 C3W 210 227
 C3Y B370 E300
 U1S 1040 1064 1068
 1336 C3L C3P
 (56) Documents cited by ISA
 GB A 1288438
 GB A 1319751
 US A 3046201
 SU A 659619
 (58) Field of search by ISA
 INT CP
 C08F 220/56
 C08L 33/26
 C12K 1/06
 INT CI C08 15/02
 C08F 29/00
 German 39c 25/01
 US-195-100
 260-89.7
 526-307
 GB 2(6) P
 C3P
 C6F FR group 14 class 5
 8 CH 37h AT 39-6 12
 14
 CA 400 401 402
 (71) Applicant
 Kievsky Meditsinsky
 Institut Imeni
 Akademika A
 A Bogomoltsa (USSR)
 252004 Kiev
 br Shevchenko d 13
 USSR
 (72) Inventors
 Vladimir Vladislavovich
 Gashinsky
 Ivan Petrovich Bilko
 Anatoly Mikhailovich
 Sokolyuk
 (74) Agent and/or Address for
 Service
 Mathisen Macara and Co

Lyon House
 Lyon Road
 Harrow
 Middlesex HA1 2ET

(54) Polyacrylamide gel for medi-
 cal and biological application and
 method of its preparation

(57) A polyacrylamide gel for medi-
 cal and biological application con-
 tains polyacrylamide and physiolog-
 ical solution with the following ratio
 of components (in % by weight):

polyacrylamide	3.0-28.0
physiological solution	72.0-97.0

The method of preparation of the
 said polyacrylamide gel comprises
 polymerization of acrylamide to-
 gether with methylene-bis-acrylam-
 ide and elution of the final product,
 both polymerization and elution be-

ing carried out in the medium of
 the physiological solution. The poly-
 acrylamide gel can be used as a
 base of nutrient mediums for grow-
 ing microorganisms, artificial crys-
 talline lenses and elastic contact
 lenses.

GB 2 114 578 A